

U.S. Application No. 10/539,014
Attorney Docket No. 2003B133D US
Response to OA of June 28, 2006
Response Dated December 8, 2006

BEST AVAILABLE COPY**List of Claims:**

1. (Currently Amended) A copolymer comprising an isoolefin and an alkylstyrene, the copolymer having a copolymer sequence distribution defined by the following equation:

$$F = 1 - \{m A / (1 + mA)\}$$

wherein m is the copolymer sequence distribution parameter; A is the molar ratio of alkylstyrene to isoolefin in the copolymer; [[and]]

F is the alkylstyrene-isoolefin-alkylstyrene triad fraction in the copolymer;

wherein m is from less than 38; and

wherein m is determined by solving said equation.

2. (Original) The copolymer of claim 1, wherein m is from less than 35.
3. (Original) The copolymer of claim 1, wherein m is from less than 30.
4. (Original) The copolymer of claim 1, wherein m is from 1-38.
5. (Original) The copolymer of claim 1, wherein m is from 1-35.
6. (Original) The copolymer of claim 1, wherein m is from 1-30.
7. (Previously presented) The copolymer of claim 1, wherein the isoolefin is isobutylene and the alkylstyrene is methylstyrene.
8. (Previously presented) The copolymer of claim 1, wherein the alkylstyrene content is from greater than 0.5 mol%.
9. (Previously presented) The copolymer of claim 1, wherein the alkylstyrene content is from greater than 1.5 mol%.
10. (Previously presented) The copolymer of claim 1, wherein the alkylstyrene content is from greater than 6.0 mol%.
11. (Previously presented) The copolymer of claim 1, wherein the alkylstyrene content is from greater than 12.5 mol%.
12. (Currently Amended) A copolymer produced by the process comprising contacting an isoolefin, preferably isobutylene, an alkylstyrene, one or more Lewis acid(s), one or more

BEST AVAILABLE COPY

U.S. Application No. 10/539,014
Attorney Docket No. 2003B133D; US
Response to OA of June 28, 2006
Response Dated December 8, 2006

initiator(s), and a diluent comprising one or more hydrofluorocarbon(s) (HFC's); the copolymer having a copolymer sequence distribution defined by the following equation:

$$F = 1 - \{m A / (1 + mA)\}$$

wherein m is the copolymer sequence distribution parameter; A is the molar ratio of alkylstyrene to isoolefin in the copolymer; [[and]]

F is the alkylstyrene-isoolefin-alkylstyrene triad fraction in the copolymer;

wherein m is from less than 38; and

wherein m is determined by solving said equation.

13. (Original) The copolymer of claim 12, wherein m is from less than 35.
14. (Original) The copolymer of claim 12, wherein m is from less than 30.
15. (Original) The copolymer of claim 12, wherein m is from 1-38.
16. (Original) The copolymer of claim 12, wherein m is from 1-35.
17. (Original) The copolymer of claim 12, wherein m is from 1-30.
18. (Previously presented) The copolymer of claim 12, wherein the alkylstyrene is methylstyrene.
19. (Previously presented) The copolymer of claim 12, wherein the alkylstyrene content is from greater than 0.5 mol%.
20. (Previously presented) The copolymer of claim 12, wherein the alkylstyrene content is from greater than 1.5 mol%.
21. (Previously presented) The copolymer of claim 12, wherein the alkylstyrene content is from greater than 6.0 mol%.
22. (Previously presented) The copolymer of claim 12, wherein the alkylstyrene content is from greater than 12.5 mol%.
23. (Previously presented) The copolymer of claim 12, wherein one or more hydrofluorocarbon(s) is represented by the formula: $C_xH_yF_z$ wherein x is an integer from 1 to 40 and y and z are integers of one or more.
24. (Original) The copolymer of claim 23, wherein x is from 1 to 10.
25. (Original) The copolymer of claim 23, wherein x is from 1 to 6.

U.S. Application No. 10/539,014
Attorney Docket No. 2003B133D US
Response to OA of June 28, 2006
Response Dated December 8, 2006

26. (Original) The copolymer of claim 23, wherein x is from 1 to 3.
27. (Original) The copolymer of claim 23, wherein the one or more hydrofluorocarbon(s) is independently selected from the group consisting of fluoromethane; difluoromethane; trifluoromethane; fluoroethane; 1,1-difluoroethane; 1,2-difluoroethane; 1,1,1-trifluoroethane; 1,1,2-trifluoroethane; 1,1,1,2-tetrafluoroethane; 1,1,2,2-tetrafluoroethane; 1,1,1,2,2-pentafluoroethane; 1-fluoropropane; 2-fluoropropane; 1,1-difluoropropane; 1,2-difluoropropane; 1,3-difluoropropane; 2,2-difluoropropane; 1,1,1-trifluoropropane; 1,1,2-trifluoropropane; 1,1,3-trifluoropropane; 1,2,2-trifluoropropane; 1,2,3-trifluoropropane; 1,1,1,2-tetrafluoropropane; 1,1,1,3-tetrafluoropropane; 1,1,2,2-tetrafluoropropane; 1,1,2,3-tetrafluoropropane; 1,1,3,3-tetrafluoropropane; 1,2,2,3-tetrafluoropropane; 1,1,1,2,2-pentafluoropropane; 1,1,1,2,3-pentafluoropropane; 1,1,1,3,3-pentafluoropropane; 1,1,2,2,3-pentafluoropropane; 1,1,2,3,3-pentafluoropropane; 1,1,1,2,2,3-hexafluoropropane; 1,1,1,2,3,3-hexafluoropropane; 1,1,1,3,3,3-hexafluoropropane; 1,1,1,2,2,3,3-heptafluoropropane; 1,1,1,2,3,3,3-heptafluoropropane; 1-fluorobutane; 2-fluorobutane; 1,1-difluorobutane; 1,2-difluorobutane; 1,3-difluorobutane; 1,4-difluorobutane; 2,2-difluorobutane; 2,3-difluorobutane; 1,1,1-trifluorobutane; 1,1,2-trifluorobutane; 1,1,3-trifluorobutane; 1,1,4-trifluorobutane; 1,2,2-trifluorobutane; 1,2,3-trifluorobutane; 1,3,3-trifluorobutane; 2,2,3-trifluorobutane; 1,1,1,2-tetrafluorobutane; 1,1,1,3-tetrafluorobutane; 1,1,1,4-tetrafluorobutane; 1,1,2,2-tetrafluorobutane; 1,1,2,3-tetrafluorobutane; 1,1,2,4-tetrafluorobutane; 1,1,3,3-tetrafluorobutane; 1,1,3,4-tetrafluorobutane; 1,1,4,4-tetrafluorobutane; 1,2,2,3-tetrafluorobutane; 1,2,2,4-tetrafluorobutane; 1,2,3,3-tetrafluorobutane; 1,2,3,4-tetrafluorobutane; 2,2,3,3-tetrafluorobutane; 1,1,1,2,2-pentafluorobutane; 1,1,1,2,3-pentafluorobutane; 1,1,1,2,4-pentafluorobutane; 1,1,1,3,3-pentafluorobutane; 1,1,1,3,4-pentafluorobutane; 1,1,1,4,4-pentafluorobutane; 1,1,2,2,3-pentafluorobutane; 1,1,2,2,4-pentafluorobutane; 1,1,2,3,3-pentafluorobutane; 1,1,2,4,4-pentafluorobutane; 1,1,3,3,4-pentafluorobutane; 1,2,2,3,3-pentafluorobutane; 1,2,2,3,4-pentafluorobutane; 1,1,1,2,2,3-hexafluorobutane; 1,1,1,2,2,4-hexafluorobutane; 1,1,1,2,3,3-hexafluorobutane; 1,1,1,2,3,4-hexafluorobutane; 1,1,1,2,4,4-hexafluorobutane; 1,1,1,3,3,4-hexafluorobutane; 1,1,1,3,4,4-hexafluorobutane; 1,1,1,4,4,4-hexafluorobutane; 1,1,2,2,3,3-hexafluorobutane; 1,1,2,2,3,4-hexafluorobutane; 1,1,2,2,4,4-hexafluorobutane; 1,1,2,3,3,4-hexafluorobutane; 1,1,2,3,4,4-hexafluorobutane; 1,2,2,3,3,4-hexafluorobutane; 1,1,1,2,2,3,3-heptafluorobutane; 1,1,1,2,2,4,4-heptafluorobutane; 1,1,1,2,2,3,4-heptafluorobutane;

U.S. Application No. 10/539,014
Attorney Docket No. 2003B133D US
Response to OA of June 28, 2006
Response Dated December 8, 2006

1,1,1,2,3,3,4-heptafluorobutane; 1,1,1,2,3,4,4-heptafluorobutane; 1,1,1,2,4,4,4-heptafluorobutane; 1,1,1,3,3,4,4-heptafluorobutane; 1,1,1,2,2,3,3,4-octafluorobutane; 1,1,1,2,2,3,4,4-octafluorobutane; 1,1,1,2,3,3,4,4-octafluorobutane; 1,1,1,2,2,4,4,4-octafluorobutane; 1,1,1,2,3,4,4,4-octafluorobutane; 1,1,1,2,2,3,3,4,4-nonafluorobutane; 1,1,1,2,2,3,4,4,4-nonafluorobutane; 1-fluoro-2-methylpropane; 1,1-difluoro-2-methylpropane; 1,3-difluoro-2-methylpropane; 1,1,1-trifluoro-2-methylpropane; 1,1,3-trifluoro-2-methylpropane; 1,3-difluoro-2-(fluoromethyl)propane; 1,1,1,3-tetrafluoro-2-methylpropane; 1,1,3,3-tetrafluoro-2-methylpropane; 1,1,3-trifluoro-2-(fluoromethyl)propane; 1,1,1,3,3-pentafluoro-2-methylpropane; 1,1,3,3-tetrafluoro-2-(fluoromethyl)propane; 1,1,1,3-tetrafluoro-2-(fluoromethyl)propane; fluorocyclobutane; 1,1-difluorocyclobutane; 1,2-difluorocyclobutane; 1,3-difluorocyclobutane; 1,1,2-trifluorocyclobutane; 1,1,3-trifluorocyclobutane; 1,2,3-trifluorocyclobutane; 1,1,2,2-tetrafluorocyclobutane; 1,1,3,3-tetrafluorocyclobutane; 1,1,2,2,3-pentafluorocyclobutane; 1,1,2,3,3-pentafluorocyclobutane; 1,1,2,2,3,3-hexafluorocyclobutane; 1,1,2,2,3,4-hexafluorocyclobutane; 1,1,2,3,3,4-hexafluorocyclobutane; 1,1,2,2,3,3,4-heptafluorocyclobutane; vinyl fluoride; 1,1-difluoroethene; 1,2-difluoroethene; 1,1,2-trifluoroethene; 1-fluoropropene; 1,1-difluoropropene; 1,2-difluoropropene; 1,3-difluoropropene; 2,3-difluoropropene; 3,3-difluoropropene; 1,1,2-trifluoropropene; 1,1,3-trifluoropropene; 1,2,3-trifluoropropene; 1,3,3-trifluoropropene; 2,3,3-trifluoropropene; 3,3,3-trifluoropropene; 1-fluoro-1-butene; 2-fluoro-1-butene; 3-fluoro-1-butene; 4-fluoro-1-butene; 1,1-difluoro-1-butene; 1,2-difluoro-1-butene; 1,3-difluoropropene; 1,4-difluoro-1-butene; 2,3-difluoro-1-butene; 2,4-difluoro-1-butene; 3,3-difluoro-1-butene; 3,4-difluoro-1-butene; 4,4-difluoro-1-butene; 1,1,2-trifluoro-1-butene; 1,1,3-trifluoro-1-butene; 1,1,4-trifluoro-1-butene; 1,2,3-trifluoro-1-butene; 1,2,4-trifluoro-1-butene; 1,3,3-trifluoro-1-butene; 1,3,4-trifluoro-1-butene; 1,4,4-trifluoro-1-butene; 2,3,3-trifluoro-1-butene; 2,3,4-trifluoro-1-butene; 2,4,4-trifluoro-1-butene; 3,3,4-trifluoro-1-butene; 3,4,4-trifluoro-1-butene; 4,4,4-trifluoro-1-butene; 1,1,2,3-tetrafluoro-1-butene; 1,1,2,4-tetrafluoro-1-butene; 1,1,3,3-tetrafluoro-1-butene; 1,1,3,4-tetrafluoro-1-butene; 1,1,4,4-tetrafluoro-1-butene; 1,2,3,3-tetrafluoro-1-butene; 1,2,3,4-tetrafluoro-1-butene; 1,2,4,4-tetrafluoro-1-butene; 1,3,3,4-tetrafluoro-1-butene; 1,3,4,4-tetrafluoro-1-butene; 1,4,4,4-tetrafluoro-1-butene; 2,3,3,4-tetrafluoro-1-butene; 2,3,4,4-tetrafluoro-1-butene; 2,4,4,4-tetrafluoro-1-butene; 3,3,4,4-tetrafluoro-1-butene; 3,4,4,4-tetrafluoro-1-butene; 1,1,2,3,3-pentafluoro-1-butene; 1,1,2,3,4-pentafluoro-1-butene; 1,1,2,4,4-pentafluoro-1-butene;

U.S. Application No. 10/539,014
 Attorney Docket No. 2003B133D US
 Response to OA of June 28, 2006
 Response Dated December 8, 2006

1,1,3,3,4-pentafluoro-1-butene; 1,1,3,4,4-pentafluoro-1-butene; 1,1,4,4,4-pentafluoro-1-butene; 1,2,3,3,4-pentafluoro-1-butene; 1,2,3,4,4-pentafluoro-1-butene; 1,2,4,4,4-pentafluoro-1-butene; 2,3,3,4,4-pentafluoro-1-butene; 2,3,4,4,4-pentafluoro-1-butene; 3,3,4,4,4-pentafluoro-1-butene; 1,1,2,3,3,4-hexafluoro-1-butene; 1,1,2,3,4,4-hexafluoro-1-butene; 1,1,2,4,4,4-hexafluoro-1-butene; 1,2,3,3,4,4-hexafluoro-1-butene; 1,2,3,4,4,4-hexafluoro-1-butene; 2,3,3,4,4,4-hexafluoro-1-butene; 1,1,2,3,3,4,4-heptafluoro-1-butene; 1,1,2,3,4,4,4-heptafluoro-1-butene; 1,1,3,3,4,4,4-heptafluoro-1-butene; 1,2,3,3,4,4,4-heptafluoro-1-butene; 1-fluoro-2-butene; 2-fluoro-2-butene; 1,1-difluoro-2-butene; 1,2-difluoro-2-butene; 1,3-difluoro-2-butene; 1,4-difluoro-2-butene; 2,3-difluoro-2-butene; 1,1,1-trifluoro-2-butene; 1,1,2-trifluoro-2-butene; 1,1,3-trifluoro-2-butene; 1,1,4-trifluoro-2-butene; 1,2,3-trifluoro-2-butene; 1,2,4-trifluoro-2-butene; 1,1,1,2-tetrafluoro-2-butene; 1,1,1,3-tetrafluoro-2-butene; 1,1,1,4-tetrafluoro-2-butene; 1,1,2,3-tetrafluoro-2-butene; 1,1,2,4-tetrafluoro-2-butene; 1,2,3,4-tetrafluoro-2-butene; 1,1,1,2,3-pentafluoro-2-butene; 1,1,1,2,4-pentafluoro-2-butene; 1,1,1,3,4-pentafluoro-2-butene; 1,1,1,4,4-pentafluoro-2-butene; 1,1,2,3,4-pentafluoro-2-butene; 1,1,2,4,4-pentafluoro-2-butene; 1,1,1,2,3,4-hexafluoro-2-butene; 1,1,1,2,4,4-hexafluoro-2-butene; 1,1,1,3,4,4-hexafluoro-2-butene; 1,1,1,4,4,4-hexafluoro-2-butene; 1,1,2,3,4,4-hexafluoro-2-butene; 1,1,1,2,3,4,4-heptafluoro-2-butene; 1,1,1,2,4,4,4-heptafluoro-2-butene; and mixtures thereof.

28. (Original) The copolymer of claim 23, wherein the one or more hydrofluorocarbon(s) is independently selected from the group consisting of fluoromethane, difluoromethane, trifluoromethane, 1,1-difluoroethane, 1,1,1-trifluoroethane, 1,1,1,2-tetrafluoroethane, and mixtures thereof.
29. (Original) The copolymer of claim 23, wherein the diluent comprises from 15 to 100 volume % HFC based upon the total volume of the diluent.
30. (Original) The copolymer of claim 23, wherein the diluent comprises from 20 to 100 volume % HFC based upon the total volume of the diluent.
31. (Original) The copolymer of claim 23, wherein the diluent comprises from 25 to 100 volume % HFC based upon the total volume of the diluent.
32. (Original) The copolymer of claim 23, wherein the diluent further comprises a hydrocarbon, a non-reactive olefin, and/or an inert gas.
33. (Original) The copolymer of claim 32, wherein the hydrocarbon is a halogenated hydrocarbon other than an HFC.

U.S. Application No. 10/539,014
Attorney Docket No. 2003B133D US
Response to OA of June 28, 2006
Response Dated December 8, 2006

34. (Original) The copolymer of claim 33, wherein the halogenated hydrocarbon is methyl chloride.
35. (Original) The copolymer of claim 23, wherein the one or more Lewis acid(s) is represented by the formula MX_4 ;
wherein M is a Group 4, 5, or 14 metal; and
each X is a halogen.
36. (Original) The copolymer of claim 23, wherein the one or more Lewis acid(s) is represented by the formula MR_nX_{4-n} ;
wherein M is Group 4, 5, or 14 metal;
each R is a monovalent C_1 to C_{12} hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;
 n is an integer from 0 to 4; and
each X is a halogen.
37. (Original) The copolymer of claim 23, wherein the one or more Lewis acid(s) is represented by the formula $M(RO)_nR'_mX_{4-(n+m)}$;
wherein M is Group 4, 5, or 14 metal;
each RO is a monovalent C_1 to C_{30} hydrocarboxy radical independently selected from the group consisting of an alkoxy, aryloxy, arylalkoxy, alkylaryloxy radicals;
each R' is a monovalent C_1 to C_{12} hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;
 n is an integer from 0 to 4;
 m is an integer from 0 to 4, wherein the sum of n and m is not more than 4; and
each X is a halogen.
38. (Original) The copolymer of claim 23, wherein the one or more Lewis acid(s) is represented by the formula $M(RC=OO)_nR'_mX_{4-(m+n)}$;
wherein M is Group 4, 5, or 14 metal;

U.S. Application No. 10/539,014
Attorney Docket No. 2003B133D US
Response to OA of June 28, 2006
Response Dated December 8, 2006

each $RC=OO$ is a monovalent C_2 to C_{30} hydrocarbacyl radical independently selected from the group consisting of an alkacyloxy, arylacyloxy, arylalkylacyloxy, alkylarylacyloxy radicals;

each R' is a monovalent C_1 to C_{12} hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;

n is an integer from 0 to 4;

m is an integer from 0 to 4, wherein the sum of n and m is not more than 4; and

each X is a halogen.

39. (Original) The copolymer of claim 23, wherein the one or more Lewis acid(s) is represented by the formula MOX_3 ;

wherein M is a Group 5 metal; and

each X is a halogen.

40. (Original) The copolymer of claim 23, wherein the one or more Lewis acid(s) is represented by the formula MX_3 ;

wherein M is a Group 13 metal; and

each X is a halogen.

41. (Original) The copolymer of claim 23, wherein the one or more Lewis acid(s) is represented by the formula MR_nX_{3-n} ;

wherein M is a Group 13 metal;

each R is a monovalent C_1 to C_{12} hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;

n is an integer from 1 to 3; and

each X is a halogen.

42. (Original) The copolymer of claim 23, wherein the one or more Lewis acid(s) is represented by the formula $M(RO)_nR'_mX_{3-(m+n)}$;

wherein M is a Group 13 metal;

each RO is a monovalent C_1 to C_{30} hydrocarboxy radical independently selected from the group consisting of an alkoxy, aryloxy, arylalkoxy, alkylaryloxy radicals;

U.S. Application No. 10/539,014
Attorney Docket No. 2003B133D US
Response to OA of June 28, 2006
Response Dated December 8, 2006

each R' is a monovalent C₁ to C₁₂ hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;

n is an integer from 0 to 3;

m is an integer from 0 to 3, wherein the sum of n and m is from 1 to 3; and

each X is a halogen.

43. (Original) The copolymer of claim 23, wherein the one or more Lewis acid(s) is represented by the formula $M(RC=OO)_nR'_mX_{3-(m+n)}$;

wherein M is a Group 13 metal;

each RC=OO is a monovalent hydrocarbacyl radical independently selected from the group independently selected from the C₂ to C₃₀ group consisting of an alkacyloxy, arylacyloxy, arylalkylacyloxy, alkylarylacyloxy radicals;

each R' is a monovalent C₁ to C₁₂ hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;

n is an integer from 0 to 3;

m is a integer from 0 to 3, wherein the sum of n and m is from 1 to 3; and

each X is a halogen.

44. (Original) The copolymer of claim 23, wherein the one or more Lewis acid(s) is represented by the formula MX_y ;

wherein M is a Group 15 metal;

each X is a halogen; and

y is 3, 4 or 5.

45. (Original) The copolymer of claim 23, wherein the one or more Lewis acid(s) is represented by the formula MR_nX_{y-n} ;

wherein M is a Group 15 metal;

each R is a monovalent C₁ to C₁₂ hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;

n is an integer from 0 to 4;

y is 3, 4 or 5, wherein n is less than y; and

U.S. Application No. 10/539,014
Attorney Docket No. 2003B133D US
Response to OA of June 28, 2006
Response Dated December 8, 2006

each X is a halogen.

46. (Original) The copolymer of claim 23, wherein the one or more Lewis acid(s) is represented by the formula $M(RO)_nR'_mX_{y-(m+n)}$;

wherein M is a Group 15 metal,

each RO is a monovalent C_1 to C_{30} hydrocarboxy radical independently selected from the group consisting of an alkoxy, aryloxy, arylalkoxy, alkylaryloxy radicals;

each R' is a monovalent C_1 to C_{12} hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;

n is an integer from 0 to 4;

m is an integer from 0 to 4;

y is 3, 4 or 5, wherein the sum of n and m is less than y; and

each X is a halogen.

47. (Original) The copolymer of claim 23, wherein the one or more Lewis acid(s) is represented by the formula $M(RC=OO)_nR'_mX_{y-(m+n)}$;

wherein M is a Group 15 metal;

each $RC=OO$ is a monovalent C_2 to C_{30} hydrocarbacyloxy radical independently selected from the group consisting of an alkacyloxy, arylacyloxy, arylalkylacyloxy, alkylarylacyloxy radicals;

each R' is a monovalent C_1 to C_{12} hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;

n is an integer from 0 to 4;

m is an integer from 0 to 4;

y is 3, 4 or 5, wherein the sum of n and m is less than y; and

each X is a halogen.

48. (Original) The copolymer of claim 23, wherein the one or more Lewis acid(s) is independently selected from the group consisting of titanium tetrachloride, titanium tetrabromide, vanadium tetrachloride, tin tetrachloride, zirconium tetrachloride, titanium bromide trichloride, titanium dibromide dichloride, vanadium bromide trichloride, tin

U.S. Application No. 10/539,014
 Attorney Docket No. 2003B133D US
 Response to OA of June 28, 2006
 Response Dated December 8, 2006

chloride trifluoride, benzyltitanium trichloride, dibenzyltitanium dichloride, benzylzirconium trichloride, dibenzylzirconium dibromide, methyltitanium trichloride, dimethyltitanium difluoride, dimethyltin dichloride, phenylvanadium trichloride, methoxytitanium trichloride, n-butoxytitanium trichloride, di(isopropoxy)titanium dichloride, phenoxytitanium tribromide, phenylmethoxyzirconium trifluoride, methyl methoxytitanium dichloride, methyl methoxytin dichloride, benzyl isopropoxyvanadium dichloride, acetoxytitanium trichloride, benzoylzirconium tribromide, benzoyloxytitanium trifluoride, isopropoxyloxytin trichloride, methyl acetoxytitanium dichloride, benzyl benzoyloxyvanadium chloride, vanadium oxytrichloride, aluminum trichloride, boron trifluoride, gallium trichloride, indium trifluoride, ethylaluminum dichloride, methylaluminum dichloride, benzylaluminum dichloride, isobutylgallium dichloride, diethylaluminum chloride, dimethylaluminum chloride, ethylaluminum sesquichloride, methylaluminum sesquichloride, trimethylaluminum, triethylaluminum, methoxyaluminum dichloride, ethoxyaluminum dichloride, 2,6-di-tert-butylphenoxyaluminum dichloride, methoxy methylaluminum chloride, 2,6-di-tert-butylphenoxy methylaluminum chloride, isopropoxygallium dichloride, phenoxy methylindium fluoride, acetoxyaluminum dichloride, benzoyloxyaluminum dibromide, benzoyloxygallium difluoride, methyl acetoxyaluminum chloride, isopropoxyloxyindium trichloride, antimony hexachloride, antimony hexafluoride, arsenic pentafluoride, antimony chloride pentafluoride, arsenic trifluoride, bismuth trichloride arsenic fluoride tetrachloride, tetraphenylantimony chloride, triphenylantimony dichloride, tetrachloromethoxyantimony, dimethoxytrichloroantimony, dichloromethoxyarsine, chlorodimethoxyarsine, difluoromethoxyarsine, acetatotetrachloroantimony, (benzoato) tetrachloroantimony, and bismuth acetate chloride.


49. (Original) The copolymer of claim 23, wherein the one or more Lewis acid(s) is independently selected from the group consisting of aluminum trichloride, aluminum tribromide, ethylaluminum dichloride, ethylaluminum sesquichloride, diethylaluminum chloride, methylaluminum dichloride, methylaluminum sesquichloride, dimethylaluminum chloride, boron trifluoride, and titanium tetrachloride.
50. (Original) The copolymer of claim 23, wherein the Lewis acid is not a compound represented by formula MX_3 , where M is a group 13 metal, X is a halogen.

U.S. Application No. 10/539,014
Attorney Docket No. 2003B133D US
Response to OA of June 28, 2006
Response Dated December 8, 2006

51. (Original) The copolymer of claim 23, wherein the one or more initiator(s) comprise a hydrogen halide, a carboxylic acid, a carboxylic acid halide, a sulfonic acid, an alcohol, a phenol, a polymeric halide, a tertiary alkyl halide, a tertiary aralkyl halide, a tertiary alkyl ester, a tertiary aralkyl ester, a tertiary alkyl ether, a tertiary aralkyl ether, an alkyl halide, an aryl halide, an alkylaryl halide or an arylalkylacid halide.
52. (Original) The copolymer of claim 23, wherein the one or more initiator(s) is independently selected from the group consisting of HCl, H₂O, methanol, (CH₃)₃CCl, C₆H₅C(CH₃)₂Cl, (2-Chloro-2,4,4-trimethylpentane) and 2-chloro-2-methylpropane.
53. (Original) The copolymer of claim 23, wherein the one or more initiator(s) is independently selected from the group consisting of hydrogen chloride, hydrogen bromide, hydrogen iodide, acetic acid, propanoic acid, butanoic acid, cinnamic acid, benzoic acid, 1-chloroacetic acid, dichloroacetic acid, trichloroacetic acid, trifluoroacetic acid, p-chlorobenzoic acid, p-fluorobenzoic acid, acetyl chloride, acetyl bromide, cinnamyl chloride, benzoyl chloride, benzoyl bromide, trichloroacetylchloride, trifluoroacetylchloride, p-fluorobenzoylchloride, methanesulfonic acid, trifluoromethanesulfonic acid, trichloromethanesulfonic acid, p-toluenesulfonic acid, methanesulfonyl chloride, methanesulfonyl bromide, trichloromethanesulfonyl chloride, trifluoromethanesulfonyl chloride, p-toluenesulfonyl chloride, methanol, ethanol, propanol, 2-propanol, 2-methylpropan-2-ol, cyclohexanol, benzyl alcohol, phenol, 2-methylphenol, 2,6-dimethylphenol, p-chlorophenol, p-fluorophenol, 2,3,4,5,6-pentafluorophenol, and 2-hydroxynaphthalene.
54. (Original) The copolymer of claim 23, wherein the one or more initiator(s) is independently selected from the group consisting of 2-chloro-2,4,4-trimethylpentane; 2-bromo-2,4,4-trimethylpentane; 2-chloro-2-methylpropane; 2-bromo-2-methylpropane; 2-chloro-2,4,4,6,6-pentamethylheptane; 2-bromo-2,4,4,6,6-pentamethylheptane; 1-chloro-1-methylethylbenzene; 1-chloroadamantane; 1-chloroethylbenzene; 1, 4-bis(1-chloro-1-methylethyl) benzene; 5-tert-butyl-1,3-bis(1-chloro-1-methylethyl) benzene; 2-acetoxy-2,4,4-trimethylpentane; 2-benzoyloxy-2,4,4-trimethylpentane; 2-acetoxy-2-methylpropane; 2-benzoyloxy-2-methylpropane; 2-acetoxy-2,4,4,6,6-pentamethylheptane; 2-benzoyl-2,4,4,6,6-pentamethylheptane; 1-acetoxy-1-methylethylbenzene; 1-acetoxyladamantane; 1-benzoyloxyethylbenzene; 1,4-bis(1-acetoxy-1-methylethyl) benzene; 5-tert-butyl-1,3-bis(1-acetoxy-1-methylethyl) benzene;

U.S. Application No. 10/539,014
Attorney Docket No. 2003B133D US
Response to OA of June 28, 2006
Response Dated December 8, 2006

64. (Previously presented) The copolymer of claim 1 or claim 12, wherein the copolymer has a Mw of from greater than 100,000.
65. (Previously presented) The copolymer of claim 1 or claim 12, wherein the copolymer has a Mw of from greater than 500,000.
66. (Previously presented) The copolymer of claim 1 or claim 12, wherein the copolymer has a Mw of from greater than 1,000,000.
67. (Previously presented) The copolymer of claim 1 or claim 12, wherein the copolymer has a MWD of from less than 3.
68. (Previously presented) The copolymer of claim 1 or claim 12, wherein the copolymer has a MWD of from 2 to 5.
69. (Previously presented) The copolymer of claim 1 or claim 12, wherein the copolymer has a Mooney viscosity of at least 20 ± 5 (ML 1 + 8 at 125°C, ASTM D 1646).
70. (Previously presented) The copolymer of claim 1 or claim 12, wherein the copolymer has a Mooney viscosity of from 20 ± 5 to 60 ± 5 (ML 1 + 8 at 125°C, ASTM D 1646).
71. (Currently Amended) A functionalized or halogenated copolymer derived from a copolymer comprising a C₄-C₇ isoolefin and an alkylstyrene represented by the formula:



wherein each R¹ and R² are independently selected from the group consisting of hydrogen, an alkyl, a primary haloalkyl, and a secondary haloalkyl; the copolymer having a copolymer sequence distribution defined by the following equation:

$$F = 1 - \{m A / (1 + mA)\}$$

U.S. Application No. 10/539,014
Attorney Docket No. 2003B133D US
Response to OA of June 28, 2006
Response Dated December 8, 2006

wherein m is the copolymer sequence distribution parameter, A is the molar ratio of alkylstyrene to isoolefin in the copolymer; [[and]]

F is the alkylstyrene-isoolefin-alkylstyrene triad fraction in the copolymer;

wherein m is from less than 38; and

wherein m is determined by solving said equation.

72. (Original) The functionalized or halogenated copolymer of claim 71, wherein m is from less than 35.
73. (Original) The functionalized or halogenated copolymer of claim 71, wherein m is from less than 30.
74. (Original) The functionalized or halogenated copolymer of claim 71, wherein m is from 1-38.
75. (Original) The functionalized or halogenated copolymer of claim 71, wherein m is from 1-35.
76. (Original) The functionalized or halogenated copolymer of claim 71, wherein m is from 1-30.
77. (Previously presented) The copolymer of claim 71, wherein the alkylstyrene content is from greater than 0.5 mol%.
78. (Previously presented) The copolymer of claim 71, wherein the alkylstyrene content is from greater than 1.5 mol%.
79. (Previously presented) The copolymer of claim 71, wherein the alkylstyrene content is from greater than 6.0 mol%.
80. (Previously presented) The copolymer of claim 71, wherein the alkylstyrene content is from greater than 12.5 mol%.
81. (Previously presented) The copolymer of claim 71, wherein the isoolefin and the alkylstyrene are present in the copolymer in amounts such that the isoolefin is from about 75.0 wt% to 99.5 wt% of the copolymer and the alkylstyrene is from about 25.0 wt% to 0.5 wt% of the copolymer (based upon the weight of the copolymer).
82. (Previously presented) The functionalized or halogenated copolymer of claim 71, wherein the isoolefin and the alkylstyrene are present in the copolymer in amounts such that the

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.